

# 3M™ Fire Barrier Sealant CP 25WB+

## Product Data Sheet

### 1. Product Description

3M™ Fire Barrier Sealant CP 25WB+ is a high-performance, ready-to-use, gun-grade, latex-based, intumescent sealant that dries to form a monolithic firestop seal that also acts as a barrier to airborne sound transmission. 3M™ Fire Barrier Sealant CP 25WB+ helps control the spread of fire, smoke and noxious gasses before, during and after exposure to a fire when installed in accordance with a listed through penetration or fire-resistive joint assembly system.

3M™ Fire Barrier Sealant CP 25WB+ firestops blank openings and penetrations passing through fire-rated floor, floor/ceiling or wall assemblies and other fire-rated interior building construction. The unique intumescent property of this material allows 3M™ Fire Barrier Sealant CP 25WB+ to expand and help maintain a firestop penetration seal for up to 4 hours as penetrants are exposed to fire. 3M™ Fire Barrier Sealant CP 25WB+ exhibits excellent adhesion to a full range of construction substrates and penetrants. No mixing is required.

#### Product Features

- Firestop tested up to 4 hours in accordance with ASTM E 814 (UL 1479) & CAN/ULC S115
- Fire Resistance tested for static construction joint systems in accordance with ASTM E 1966 (UL 2079)
- Re-enterable / repairable
- Meets UL 1479 aging requirements
- Helps minimize sound transfer\*
- Applied with conventional caulking equipment (excellent caulk rate)
- Extensive listed systems
- Sag-resistant
- Halogen-free
- Excellent adhesion
- Paintable
- Water clean up



High-performance firestop sealant that also helps minimize sound transfer

Product Color: ■ Red

*Meets the intent of LEED® VOC regulations — helps reduce the quantity of indoor air contaminants that may be odorous, irritating and harmful to the comfort and well-being of the installers and occupants. <250 g/L VOC contents (less H<sub>2</sub>O and exempt solvents).*

*\*Minimizes noise transfer — STC-Rating of 54 when tested in STC 54-rated wall assembly.*

### 2. Applications


High-performance 3M™ Fire Barrier Sealant CP 25WB+ is ideal for sealing single or multiple through penetrations in fire-rated construction. 3M™ Fire Barrier Sealant CP 25WB+ is typically used in mechanical, electrical and plumbing applications to firestop openings created by the following penetrations in fire-rated floors, floor/ceilings or walls: metallic pipe, plastic pipe (excluding CPVC), conduit, power and communication cable, cable trays, busways, combos, insulated pipe and HVAC duct penetrations 3M™ Fire Barrier Sealant CP 25WB+ is also used to firestop blank openings and static construction joints.

### 3. Specifications

3M™ Fire Barrier Sealant CP 25WB+ shall be a one component, ready-to-use, gun-grade, latex-based, intumescent firestop sealant capable of expanding a minimum of three times its dried volume when exposed to temperatures above 1000°F (538°C). The material shall be thixotropic and shall be applicable to overhead, vertical and horizontal firestops. The sealant shall be listed by independent test agencies such as UL, Intertek or FM. 3M™ Fire Barrier Sealant CP 25WB+ shall be tested to and pass the criteria of ASTM E 814 (UL 1479) Standard Test Method for Fire Tests of Penetration Firestop Systems, ASTM E 1966 (UL 2079) Standard Test Method for Fire Resistive Joint Systems and CAN/ULC S115 Standard Method of Fire Tests of Firestop Systems. 3M™ Fire Barrier Sealant CP 25WB+ meets the requirements of the IBC, IRC, IFC, IPC, IMC, NFPA 5000, NEC (NFPA 70) and NFPA 101.

**Typically Specified Division**  
Division 7  
Section 07 84 00 – Firestopping

**Related Sections**  
Section 07 84 16 – Annular Space Protection  
Section 07 84 43 – Fire-Resistant Joint Sealants  
Section 07 86 00 – Smoke Seals  
Section 07 87 00 – Smoke Containment Barriers  
Section 07 27 00 – Air Barriers  
Section 21 00 00 – Fire Suppression  
Section 22 00 00 – Plumbing  
Section 26 00 00 – Electrical



FILL, VOID OR CAVITY MATERIAL FOR USE IN THROUGH-PENETRATION FIRESTOP SYSTEMS  
SEE UL FIRE RESISTANCE DIRECTORY 9069



**LISTED**

FILL, VOID OR CAVITY MATERIALS 9069



SUBJECT TO THE CONDITIONS OF APPROVAL AS A WALL & FLOOR PENETRATION FIRESTOP WHEN INSTALLED AS DESCRIBED IN THE CURRENT EDITION OF THE FMRC APPROVAL GUIDE



**Intertek**  
FIRESTOP SYSTEMS  
SEE INTERTEK DIRECTORY



**Intertek**  
FIRESTOP SYSTEMS  
SEE INTERTEK DIRECTORY

## 4. Physical Properties

|   |  |  |                   |
|---|--|--|-------------------|
| <b>Color:</b>                                       | Red  | <b>Hardness (ASTM D 2240 Shore A):</b>   | 45                |
| <b>Application Temperature Range (ASTM C 1299):</b> | 40° to 122°F (4° to 50°C)                    | <b>Tensile Strength:</b>   | 85 psi (0.59 MPa) |
| <b>Service Temperature Range:</b>                   | -20° to 180°F (-28° to 82°C)                 | <b>Volume Shrinkage (ASTM C 1241):</b>   | 28%               |
| <b>STC (ASTM E 90 and ASTM E 413):</b>              | 54 when tested in STC 54-rated wall assembly | <b>VOC Less H<sub>2</sub>O and Exempt Solvents:</b>  | < 1g/L            |
| <b>Surface Burning (ASTM E 84):</b>                 | Flame Spread 0, Smoke Development 0          | <b>Dry:</b> Under typical conditions of 75°F (23°C) and 50% relative humidity, sealant becomes tack-free in about ten minutes and dry-to-touch in 30–60 minutes. Full dry depends upon ambient conditions and volume of sealant. Typical dry rate is approximately 1/8-inch (3mm) per day. |                   |

Unit Volume: 10.1 fl. oz. tube (298.7mL, 18.2 in.<sup>3</sup>), 20 fl. oz. sausage (591.5mL, 36.1 in.<sup>3</sup>), 27 fl. oz tube (798.5mL, 48.7 in.<sup>3</sup>), 2 gallon pail (7.57L, 462 in.<sup>3</sup>), 5 gallon pail (18.9L, 1155 in.<sup>3</sup>)

## 5. Packaging, Storage, Shelf Life

|                    |  |
|--------------------|--|
| <b>Packaging:</b>  | Product packaged in cartridge or pail is enclosed in HDPE plastic containers, sausage is packaged in aluminum foil wrap.   |
| <b>Storage:</b>    | 3M™ Fire Barrier Sealant CP 25WB+ should be stored indoors in dry conditions between 40°F and 90°F (4°C and 32°C) in the original unopened package. Avoid repeated freeze / thaw exposures of the 3M™ Fire Barrier Sealant CP 25WB+ prior to installation.   |
| <b>Shelf Life:</b> | 3M™ Fire Barrier Sealant CP 25WB+ shelf life is 12 months in original unopened containers from date of packaging when stored above 68°F (20°C).<br>Lot numbering (e.g. 8183AS): First digit = Last digit of year manufactured, Second to fourth digit = Julian Date, Letters = Random to distinguish between lot numbers |

## 6. Installation Techniques

*Consult a 3M Authorized Fire Protection Products Distributor / Dealer or Sales Representative for Applicable UL, Intertek or other third-party drawings and system details.*

|                              |  |
|------------------------------|--|
| <b>Preparatory Work:</b>     | The surface of the opening and any penetrating items should be cleaned to allow for the proper adhesion of the 3M™ Fire Barrier Sealant CP 25WB+. Ensure that the surface of the substrates are not wet and are frost free. Sealant can be installed with a standard caulking gun, pneumatic pumping equipment or it can be easily applied with a putty knife or trowel.   |
| <b>Installation Details:</b> | Install the applicable depth of backing material, if required, as detailed within the applicable UL, Intertek, FM or other third-party listed system. Cut the end of the 3M™ Fire Barrier Sealant CP 25WB+ tube spout to achieve the desired bead width when applying. Install the applicable depth of 3M™ Fire Barrier Sealant CP 25WB+ into the opening flush with the surface of the substrate, or as detailed within the applicable listed system, at the depth for the assembly and rating that is required. Tool within five minutes. Clean all tools immediately after use with water.  |
| <b>Limitations:</b>          | Do not apply 3M™ Fire Barrier Sealant CP 25WB+ when surrounding temperature is less than 40°F (4°C) and in conditions where seals may be exposed to rain or water spray within 18 hours of application. Do not apply 3M™ Fire Barrier Sealant CP 25WB+ to building materials that bleed oil, plasticizers or solvent (e.g. impregnated wood, oil-based sealants, or green or partially vulcanized rubber). Do not apply 3M™ Fire Barrier Sealant CP 25WB+ to wet or frost-coated surfaces or to areas that are continuously damp or immersed in water.<br><b>NOTICE: This product is not acceptable for use with chlorinated polyvinylchloride (CPVC) pipes.</b> |

## 7. Maintenance

No maintenance should be required when installed in accordance with the applicable UL, Intertek, FM or other third-party listed system. Once installed, if any section of the 3M™ Fire Barrier Sealant CP 25WB+ is damaged, the following procedure will apply: remove and reinstall the damaged section in accordance with the applicable listed system, with a minimum 1/2 in. (12.7mm) overlap onto the adjacent material.

## 8. Availability

3M™ Fire Barrier Sealant CP 25WB+ is available from 3M Authorized Fire Protection Products Distributors and Dealers. 3M™ Fire Barrier Sealant CP 25WB+ is available in 10.1 fl. oz. cartridges (12/case), 20.0 fl. oz. sausages (10/case), 27.0 fl. oz. cartridges (6/case), 2 gallon pails (1/case) and 5 gallon pails (1/case). For additional technical and purchasing information regarding this and other 3M™ Fire Protection Products, please call: 1-800-328-1687 or visit [www.3M.com/firestop](http://www.3M.com/firestop).

## 9. Safe Handling Information

*Consult product Material Safety Data Sheet (MSDS) prior to handling and disposal.*

7A Ashlesha Apartment, Lotus Residency Lane,  
Off, Late GA Kulkarni Path, near Subway,  
near Karishma Complex, Kothrud,  
Pune, Maharashtra 411038  
[ecotechinnovationspune@gmail.com](mailto:ecotechinnovationspune@gmail.com)

